

## KERAGREEN SUNFLOWER MOULDED

### **Description:** KERAGREEN Cast Sunflower Vegetable Wax

#### **Technical Specifications:**

	Method	Unit	Values
Congealing point	ASTM D 938	°C	54 - 60
Drop Melting Point	ASTM D 3954	°C	57 - 65
Kinematic Viscosity at 100°C	ASTM D 445	Cst	9-14
Penetration at 25°C	ASTM D 1321	1/10mm	25 - 35
Colour	VISUAL		
	1		

#### **Properties:**

Makes very white candles that can be easily colored.

No shrinkage or crystallization on cooling.

No bad smell when burning or quenching, Produces a very soft flame and a long burn time depending on the type of wicks associated.

#### Storage and preservation:

Protect from the sun, dust and excessive temperatures. Store in cool, dry places.

#### **Presentation:**

Waxy solid of white colour and neutral odour, presented in a 20 kg case and Waxy solid ivory coloured and neutral odour, presented in pearls.

#### Packaging:

This product is delivered in pellets in 20kg boxes.

26 février 2025

## Active

Phone: + 33 (0) 4 75 54 35 05

# **Distribution C** ompany

Email: contact@adc-solution.com

SIREN: 432 961 134 SIRET: 432 961 134 00041 40 Impasse des Jones D 126 route d'Allan 26780 Malataverne ADC France with a capital of 163,200 Euros – RCS 432 961 134 VALENCE – VAT FR 64 432 961 134